

58. (NEW) A heat shield as in recited in claim 49, wherein the thickness of said insulating material positioned between said first and second plate is varied at different locations between said first and second plate.

59. (NEW) A heat shield as recited in claim 49, wherein predetermined portions of the heat shield are kept free of said insulating material.

REMARKS


Prior to a formal examination of the above-identified application, acceptance of the new claims and the enclosed substitute specification (under 37 CFR 1.125) is respectfully requested. It is believed that the substitute specification and new claims will facilitate processing of the application in accordance with M.P.E.P. 608.01(q). The substitute specification and new claims are in compliance with 37 CFR 1.52 (a and b) and, while making no substantive changes, are submitted to conform this case to the formal requirements and long-established formal standards of U.S. Patent Office practice, and to provide improved idiom and better grammatical form.

The enclosed substitute specification is presented herein in both marked-up and clean versions.

STATEMENT

The undersigned, an attorney registered to practice before the office, hereby states that the enclosed substitute specification includes the same changes as are indicated in the mark-up copy of the original specification. The substitute specification contains no new subject matter.

Respectfully submitted,


Michael B. Stewart (Reg. No. 36,018)
John P. Guenther (Reg. No. 39,698)
RADER, FISHMAN & GRAUER PLLC
1533 N. Woodward Ave., Suite 140
Bloomfield Hills, Michigan 48304
(248) 594-0633
Attorney for Applicants

CERTIFICATE OF MAILING

I hereby certify that the enclosed Preliminary Amendment is being deposited with the United States Postal Service on the date shown below with sufficient postage as Express Mail Post Office to Addressee mailing Label Number EL 429915448US in an envelope addressed to the: Commissioner of Patents and Trademarks, Washington, D.C. 20231.

Date: 9-29-99

By: Stephanie A. Scash

R0062757

60680-1281 (4908 REIN)

SUBSTITUTE SPECIFICATION: MARKED UP COPY

[Method for manufacturing a heat shield and a heat
shield manufactured with the method]

HEAT SHIELD AND METHOD FOR MANUFACTURING THE SAME

FIELD OF THE INVENTION

5 The present invention relates to a heat shield that is suitable for use in connection with a motor vehicle and a method for manufacturing the same. [method and a heat shield produced with this method according to the preamble of patent claim 1.] The [correspondingly manufactured] heat shield is intended to [be suitable for use in motor vehicles and to] protect [there] temperature-sensitive assemblies,
10 components and connection lines from the direct impact of [in such a way that] heat radiation. [cannot impact directly and,] [m]Moreover, the heat shield acts as insulation. Furthermore, the present invention [it] is intended to provide[have favourable] sound-proofing qualities.

BACKGROUND OF THE INVENTION

15 The need for the use of heat shields has greatly increased in motor vehicles. This is essentially caused by the fact that the space available in the engine compartments of motor vehicles has to be exploited to the maximum in order to accommodate the assemblies, components and connection lines necessary for operation, such that these parts have to be arranged very close to one another. This leads to heat-
20 sensitive components having to be arranged very close to very hot components, such as for example the exhaust system, the combustion engine or the heat exchanger. The heat radiated by these elements can [activate]adversely affect the functioning of the heat-sensitive components. To this end, the heat-sensitive elements or components are protected from the heat radiation and the high
25 temperatures by heat shields arranged in front of them.

[From] DE 38 34 054 C2 discloses [is known] a [correspondingly configured] heat shield, in which, in order to protect from heat radiation, at least two flat materials are used which are connected to one another on at least two edge regions turned away from one another. The flat materials mentioned are connected to one another in such a way that a gap is formed between them. Moreover, with this known heat shield it is important that the flat material facing the source of the heat radiation is so oriented in its expansion characteristic by pre-determined profiling or beading or corresponding choice of material that it expands towards the heat source. Through corresponding configuration, adaptation to the heat load arising should be made possible, since with higher temperatures the spacing of the two flat materials used, which should preferably consist of sheet metal is increased and an enlarged air gap is produced which naturally improves the insulation effect.

The heat shield described in DE 38 34 054 C2 can then be further improved in relation to its insulating effect if a heat insulation layer is applied in addition to the inner surfaces of the flat materials proposed there. [As] [s] Suitable insulating materials may include [are here proposed] organic or inorganic fibre materials, but also metallic woven fabrics, knitted fabrics or expanded metals (grids), which are also intended to improve the soundproofing.

The heat shield described therein has a substantial disadvantage in the fact that it is not possible for every conceivable contour of the heat shield to be configured [, in order] to achieve the desired effect for adaptation to the different temperatures.

Moreover, the insulation effect is limited if only an air gap is used without additional heat-insulating materials.

If on the other hand, as explained already, heat-insulating layers are applied, then in return increased manufacturing outlay is incurred [has to be put up with]. For the application of the heat-insulating materials as a heat-insulating layer, binding

agents are necessary. However, such binding agents [which] generally have organic components which cause problems at the high temperatures.

Furthermore, in DE 39 05 871 C2, a compound material for heat insulation and sound proofing for screening parts and heat shields in the automobile field are
5 described. An insulation layer, consisting of a thermally resistant highly porous inorganic material is [here] used which is enclosed on at least one side with a stabilising, structurally fixed covering layer, preferably a metal foil. This covering layer surrounds the insulation layer in one example completely, or, in the case where the compound material, formed from an insulation layer and the covering
10 layer, is disposed on the surface of a screening part, on the side turned away from the surface of the screening part.

For the insulation layer, various inorganic materials are mentioned which are preferably foamable (water glass, foamed glass, glass concrete, foamed ceramic or clay mineral materials) and thermally resistant reinforcing fibres or flakes (mica or
15 graphite). The insulation layer of the compound material described there should be manufactured by foaming of a suitable material. The foamed material is then surrounded with the covering layer already mentioned. Here, besides the relatively high manufacturing outlay, what has proved disadvantageous is that the foamed material has, after it has hardened, a specific shape which can only be altered
20 slightly or with additional outlay. This leads to problems and to increased technological outlay in the manufacture of heat shields, when more complicated shapes are necessary for same.

[From] DE 39 05 871 C2 discloses a concept of adding thermally resistant fibres or flakes (mica or graphite) [can be taken the idea that] to the actual insulation layer
25 material [should be added thermally resistant fibres or flakes (mica or graphite)]. Such fibres or flakes [which] are intended to improve in particular the mechanical properties.

A further disadvantage of heat shields manufactured according to this theory consists in the fact, that greater forces acting on these heat shields can lead to deformations, or even to rupturing of the insulation layer material. This can lead to impairment of the actual functioning, and in conjunction with vibrations, to noise.

- 5 Moreover, it must be guaranteed that the composite material described in DE 39 05 871 C2 is surrounded by outer covering layers and a connection with the screening part must be ensured, which prevents vibrations occurring which can lead to annoyance caused by noise.

- 10 Proceeding from the above, an[the] object of the present invention is to propose a method and a heat shield manufactured with this method, the method being intended to be simple and able to be carried out at a favourable cost, and the heat shield manufactured with this method being safe from a [every] toxicological and ecological point of view.

SUMMARY OF THE INVENTION

- 15 [According to the invention, this object is achieved with the features of patent claim 1 for the method and with the features of claim 21 for the heat shield manufactured with the method. Advantageous embodiments and developments of the invention arise with the use of the features mentioned in the subordinate claims.]

- 20 For the manufacture of a heat shield according to the present invention, insulating material in powder or flake form is used. This insulating material is applied loose to a plate which consists of at least one material which is partially plastically deformable. Here it is possible for only one portion of the surface to be covered by the insulating material. In particular, the edge regions or the regions for apertures
25 (screw holes) of the plate should be kept free.

Vermiculite, a decomposition product of mica, has proved to be particularly suitable as an insulating material. But mica itself can also be used, or expanded graphite or perlite. It is also possible to add fillers to the insulating material, such as sand for example.

5 Following the trickling-on process, a second plate with a pressing tool, or a pressing tool on its own, is moved towards the sprinkled surface of the first plate, and the insulating material, trickled loose onto the first plate, is if necessary distributed, and after a sufficient compressive force has been applied to the insulating material by means of the two plates or the pressing tool, in one or more
10 pressing cycles, and compaction of the insulating materials has been achieved at least in regions, the two plates are connected to one another in their edge regions. The procedure can also be such that the compressing of the insulating material takes place after the feeding of the two plates in the direction of the first plate shortly before the connection in the edge region takes place, i.e. the compaction is
15 a separate step. It is not absolutely necessary [here] for the edge to be completely closed. For connecting the two plates to one another, suitable positive and/or non-positive connections can be considered. However it has been shown that flanging of the edges on at least two opposite sides of the plates to be connected to one another is sufficient. Reliable enclosure of the insulating material between the two
20 plates is however given if the edges are flanged on all sides.

The method according to the invention can, however, also be carried out in such a way that, after the loose application of insulating material on the first plate, for example with a pressing tool, the insulating material is compacted and thereafter pre-determinable regions can be deliberately provided with additional insulating
25 material in a loose form, which regions are then in turn compacted under pressure applied with a second pressing tool, which can be correspondingly contoured, or with the second plate. By this means, regions of the heat shield can be deliberately so manufactured that they have on the one hand higher compaction and on the

other hand increased thickness, so that the desired properties can be deliberately influenced, also taking into consideration the sound proofing.

The process can be carried out very simply, and thus it is possible for the insulating material to be distributed with a suitable conveying or feeding device more or less evenly on the first plate. Storage containers in the form of hoppers with an aperture can, for example, serve as feeding devices. From this hopper the insulating material can be applied to a conveyor belt, from which it is then led onto the first plate. Application from the hopper via two counter-rotating rollers is also possible. Doctor blades can also be arranged at suitable points. A second variant consists in the fact that the insulating material used is so trickled on that a cone of material forms, which then, proceeding from the top of the cone, is pressed together with the second plate or a pressing tool, and thus the insulating material is distributed.

The place where the cone of material is formed can then be so selected that optimum distribution of the insulating material between the two plate-shaped structures is produced. Normally this will be the area centre of mass of the plate, on which the insulating material is trickled. The arrangement of the cone of material on the plate can however also be adjusted to conditions which may be necessary, such as the final shape of the heat shield to be manufactured or taking into account a special region which has to have an increased insulating effect.

In the distribution of the insulating material in powder or flake form, it is advantageous that here no binding agent has to be added and the individual grains or flakes can be distributed almost unhindered. Avoiding a binding agent has furthermore the advantage that no ecological and toxicological aspects have to be taken into account in the manufacture and use of the heat shields manufactured according to the invention, and there are also no problems in disposal.

Before the insulating material is trickled on, the first plate can be deformed at least partially trough-shaped, in order to prevent the insulating material trickled onto it from being lost. The deformation is preferably undertaken at the edges and can then be used subsequently in the actual connection of the two plates, between
5 which the insulating material is to be received.

Losses of insulating material after trickling-on, can, moreover, be prevented, or at least reduced, if before the trickling-on of the insulating material, the surface on the first plate, which forms the base for the cone of material, is provided with an inorganic binding agent, preferably water glass, which is physiologically and
10 ecologically safe.

Moreover, the distribution of the insulating material between the two plates can be deliberately influenced by recesses protrusions being worked in, into which a greater volume of insulating material can be received and consequently the insulating capacity of the heat shield can there be locally increased, which can be
15 advantageous for certain uses. A further possible way of influencing the distribution of the insulating material in specific regions of the heat shield can, however, also be achieved in that beads and/or webs are present on at least one of the two plates or on a pressing tool, which on the one hand can receive more insulating material or, on the other hand, the webs are so configured that insulating
20 material, after being trickled on, can be displaced deliberately from specific regions, or specific regions, (e.g. regions with screw holes) can be more strongly compacted.

According to the invention, however, it is also possible for the process to be carried out in such a way, that after the loose application of the insulating material, the
25 compaction is carried out with a pressing tool, provided with recesses or apertures, or respectively a stepped pressing tool, such that non-compacted regions are formed, from which the loose insulating material can subsequently be removed. These regions should preferably be formed where for example screw holes are

provided for fastening the heat shield. The removal of the non-compacted insulating material can here come about in simple manner through blowing away or through suction.

5 A further possible way of configuring regions which are to be kept free of insulating material consists in, before the loose application of the insulating material, certain regions on the first plate, which can also be pre-determined, being electrostatically charged, and, after the application of the insulating material, the latter being removed from the non-charged regions. Following the removal of the undesired insulating material, the retained insulating material can then be
10 compacted, as already described, and thereafter covered with the second plate.

In contrast thereto, however, there also exists the possibility of applying insulating material loose to the first plate and then removing it again with a tool which is electrostatically charged in regions. For this purpose, a plate-shaped element, but also a drum-shaped element, can be charged electrostatically on the surfaces,
15 correspondingly in regions.

Thereafter the remaining insulating material, can be compacted as already described.

It is advantageous so to form especially edge regions, regions with narrow radii, that at least the amount of insulating material in these regions is reduced.

20 Since the heat shield, after the connection of the two plates, is not a rigid body, and the plates generally consist advantageously of a metal, additional three-dimensional deformation can easily be undertaken, and in this way the finally desired contour, which is optimally adapted to the necessary fitting circumstances in the engine compartment of a motor vehicle, are achieved. In this deformation,
25 no problems occur through the enclosed insulating material, since no or at least only low binding forces between the individual grains or flakes have to be broken

up, and the latter slide past one another only slightly hindered during the deformation, and the new shape can be achieved.

Moreover, [Foregoing] a binding agent provides a further [has furthermore the] advantage in that [especially] the soundproofing properties of the heat shield can
5 be improved, since the soundwave energy can be very well decomposed with the aid of the mica in powder or flake form, and also there is no resultant long-term impairment. Naturally, there are also no resonance problems which could lead to increased noise impairment.

However it can also be advantageous if at least one of the two plates has increased
10 surface roughness on the surface which comes into direct contact with the insulating material, since this has a positive effect on the distribution of the insulating material during the movement of the second plate onto the first plate and increased adhesion of the insulating material after being trickled on counteracts any undesired falling of insulating material.

15 In order to improve the effect of the heat shield, it is moreover advantageous if at least one of the plates is used with a coating applied on at least one side and reflecting the heat radiation. This coating should preferably be orientated towards the heat source.

To carry away heat, it is advantageous if the plate which is disposed on the side
20 turned away from the heat source is thicker, and provided with ribs and/or consists of a material with good heat-conducting capacity, such that the received heat can be led away well.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention is [to be] described below in greater detail with reference to the
25 following drawing figures [the aid of embodiments. The figures show here]:

Fig. 1 is a top perspective view of an embodiment of the present invention illustrating a first plate and an insulating material positioned on said plate. [an amount of insulating material trickled onto a plate];

Fig. 2 a sectional view of an embodiment of a heat shield manufactured in accordance with one aspect of [according to] the present invention;

Fig. 3 is a top perspective view of a first plate and a side elevation view of a second plate that [a front elevation of a plate for an embodiment of a heat shield according to the invention and a second plate which] may be connected [to the first plate] to form a heat shield; [,] and

Fig. 4 is a [further embodiment in] partial sectional view of another embodiment of a heat shield formed in accordance with another aspect of the present invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

[In] Fig. 1 illustrates an embodiment of the present invention in which [is shown how] a first plate 1 has been sprinkled with insulating material (mica in powder and/or flake form) on a portion of a surface which is configured practically flat. The sprinkling with the insulating material 3, in this example, took place by forming a cone of the material. [,] [this] The sprinkling can however take place over a somewhat larger surface. The edge regions or other regions of the plate 1 should preferably be deliberately not sprinkled or subsequently freed of insulating material 3.

[On]In the embodiment shown in this figure, the edges of the plate 1 are bent upwards, in order to prevent sideways falling of insulating material 3. There is, however, also the possibility, which is not shown in this figure, of bending over the front edges of the plate 1 and producing a complete trough shape.

The arrow shown in Fig. 1 indicates the direction in which a second plate 2, not shown, is pressed towards the first plate 1. The pouring of the insulating material 3 is distributed relatively evenly with the movement of the non-represented plate 2, and in preferred form, the pressing force and the amount (especially the volume) of the trickled-on insulating material should be matched to one another in such a way that after the two plates have been connected, the insulating material 3 completely fills the space between the first plate 1 and the second plate 2.

The section, shown in Fig. 2, through an example of a heat shield configured according to the invention, then shows how the edges of the first plate 1 can bend over the front edges of the second plate 2, and thus the connection of the two plates 1 and 2 can be produced. The flanged region is then suitable for the mounting of the finished heat shield and the engagement of suitable fastening elements.

On the example shown in Fig. 2, the deformation of the first plate 1 occurs exclusively to connect it with the second plate 2, and the second plate 2 is deformed during pressing against the first plate 1 as a result of the limited incompressibility of the insulating material 3. This can be achieved by suitable contouring of the pressing tool in connection with the already-mentioned optimised measurement of the volume of the insulating material to be used. Naturally, however, the first plate 1 can also be deformed correspondingly, if it is disposed in a correspondingly contoured die.

[In] Fig. 3 illustrates [are represented] two possible embodiments for the first plate 1 and the second plate 2.

[Here]In Fig. 3, the first plate 1 is provided with bulges 5, which are disposed locally in such a way that specific regions, in which the thermal load has to be particularly reduced, can be taken into account. In the manufacture according to the present invention of such a heat shield, a larger amount of insulating material 3

is then distributed into the bulges 5, and consequently the insulating effect of the heat shield is increased [there].

The second plate 2, which is represented in Fig. 3, is provided with a bead 6 which, during the manufacture of the heat shield according to the present invention, can likewise deliberately influence the distribution of the trickled-on insulating material 3, since insulating material 3 is displaced in the region of the bead 6. Instead of the bead 6, however, a web can also be used.

The configurations of the bulges 5 or those of one or more beads 6 have, moreover, the advantage that the stability of the heat shield can be additionally increased.

10 The first and second plates 1 and 2, shown in Fig. 3, can be used both individually and together to manufacture a heat shield according to the present invention, the embodiments then not having to be limited to the configuration and arrangement shown, but, for example, a crosswise arrangement of a plurality of beads or webs can be used.

15 Fig. 4 shows a further embodiment of a heat shield configured according to an aspect of the present invention, in partial sectional view, in which in particular the part is shown in which a screw hole 7 is formed.

[Here,] [d]During the manufacture of this heat shield, the process is such that the region of the screw hole 7 is left free when the insulating material 3 is applied, or this region, as referred to in more detail in the specification already, is freed after the application of insulating material 3. Thereafter, there is compaction of the insulating material with a pressing tool in at least one working cycle, and after this first compaction, insulating material is, in this example, applied again in a circular manner around the screw hole 7, and thereafter the second plate 2 is pressed with a correspondingly contoured pressing and stamping tool against the insulating material 3, towards the first plate 1. Here, particularly the insulating material 3 subsequently applied in region 8 is compacted, and the two plates 1 and 2 are

correspondingly deformed, the first plate 1 being advantageously disposed on a correspondingly configured die for this purpose. The pressing tool to be used stamps in the same working cycle the actual screw hole 7 in the heat shield and it is thus possible to produce, with relatively low manufacturing outlay, a very
5 advantageous embodiment of a heat shield according to the invention, in which a through-hole 7 has to be present for fastening or for other purposes. The material accumulation in region 8 here causes substantially better heat and sound insulation in this particularly critical region.

Abstract

A heat shield suitable for motor vehicles and a method for manufacturing the heat shield is provided. [The invention relates to a method and a heat shield
5 manufactured with the method.] The [correspondingly produced] heat shield is intended [to be particularly suitable for use in motor vehicles and] to protect [there] temperature-sensitive assemblies, components and connection lines from the direct impact of [in such a way that] heat radiation [cannot impact directly] and, possibly, [moreover, the heat shield] acts as insulation. Moreover, the heat shield
10 may also provide [it is intended to have] advantageous soundproofing properties. The heat shield is comprised of first and second plates that are at least partially deformable and an insulating material positioned between said plates. Preferably, at least a portion of said insulating material is in the form of compacted powder or flakes. [In the heat shield, insulating material is applied loose in powder form,
15 between two plates which are at least partially plastically deformable, onto one of the two plates (1,2) covering it at least partially, then is compacted under pressure at least in regions, and then the second plate (2), in a position lying above the insulating material (3), is connected with the first plate (1) through a positive or non-positive connection of the plates (1, 2) in their edge regions.]

20

r0063995